

Current	Micrometal 60#1	Microemtal 60#2	Curie SF53-200#1	Curie SF53-200#2
0	783.7	788.1	778.1	803.4
5	763.3	766.8	778.0	800.4
10	706.0	707.0	729.5	747.8
15	642.7	645.0	668.8	686.2
20	584.1	582.0	608.0	623.2
24	540.0	544.0	566.8	580.9

% change (0-24A) 31.09% 30.97% 27.16% 27.69%

