

# CURIE IRON POWDER MATERIAL PROPERTY

## GENERAL MATERIAL PROPERTIES

Materials	Initial Permeability $\mu_i$	Permeability with DC Bias $H_{dc}=50$ Oersted @ 10KHz
90	90	38 (42%)
75H	75	44 (59%)
75	75	38 (50%)
60	60	37 (62%)
55	55	40 (72%)
35	35	30.8 (88%)
33	33	28 (85%)
23	23	20.7 (90%)
SF53	53	44 (76%)

## INITIAL PERMEABILITY V.S. FREQUENCY

